

	FINORCHEM LIMITED			Doc. No.: FM12/PDS/ADL/007
	FINISHED PRODUCT- PDS			Page 1 of 1
	Issue No.: 02	Issue Date: 04/07/2024	Rev. No.: 01	Eff. Date: 05/07/2024

FINOREX KR-140

DESCRIPTION

Super tackifying agent

TYPICAL PROPERTIES

Sr. No.	Property	Unit	Specification		Test Method
			Min	Max	
1.	Appearance	-	Yellow to dark brown colour Pastille/Flakes		Visual
2.	Softening point (R&B)	°C	135	150	ASTM E28
3.	Ash content, 750±25°C	%w/w	-	1.0	ASTM D4574
4.	Zinc content	%w/w	0.30	0.60	QC/STP/U2/166
5.	Specific Gravity at 25°C	-	0.95	1.10	ASTM D1817

RECOMMENDED APPLICATIONS:

- Finorex KR 140 resin offers superior tack properties under severe environment conditions. Better tackifier than PTOP resin, offers high & long-term tackiness, improves runner extrudability and improved resistance of rubber goods made from natural or synthetic rubbers to aging caused by exposure to heat & dynamic load. Used in Various Cushion compounds exposed at severe loading conditions.

PACKAGING

- 25 Kg in HDPE liner with paper bag / carton packing.

STORAGE

- Finorex KR-140 is a stable resin and can be stored for 12 months from the date of manufacture under normal storage conditions. Need to store below 30°C in tight container away from heat and humidity.

OCCUPATIONAL SAFETY AND HEALTH INFORMATION

- Refer to Material Safety Data Sheets (MSDS) prior to using this resin.

Corporate Office :

Finorchem Limited
9E, Saket Apartment, 2 Ho Chi Minh Sarani,
9th Floor Kolkata-700 071
+91-33-40634254, Corporate@finorchem.com