

	FINORCHEM LIMITED			Doc. No.: FM12/PDS/ADL/030
	FINISHED PRODUCT- PDS			Page 1 of 1
	Issue No.: 02	Issue Date: 04/07/2024	Rev. No.: 01	Eff. Date: 05/07/2024

FINOREX PT

DESCRIPTION

Polyterpene resin. Tread enhancement additive-TEA Resin.

PRODUCT SPECIFICATION

Sr. No.	Property	Unit	Specification		Test Method
			Min	Max	
1.	Appearance	-	Light yellow to reddish brown colour pastles/flakes		Visual
2.	Softening point (R&B)	°C	110	120	ASTM E28
3.	Ash content, 750±25°C	%w/w	-	0.50	ASTM D4574
4.	Loss on drying at 105°C	%w/w	-	0.50	ASTM D4571
5.	Specific Gravity at 25°C	-	0.85	1.00	ASTM D1817

RECOMMENDED APPLICATIONS

Finorex PT, modify the viscoelastic nature of polymer by increasing compound Tg and offers improved traction and marginal reduction in rolling resistance. Finorex PT used in automobile tires and pressure sensitive adhesives.

PACKAGING

25 Kg in HDPE liner with paper bag / carton packing.

STORAGE

Finorex PT resin recommends storage temperatures below 35°C, this material is a stable resin and can be stored for 12 months from the date of manufacture.

OCCUPATIONAL SAFETY AND HEALTH INFORMATION

Refer to Material Safety Data Sheets (MSDS) prior to using this resin.

Corporate Office:

Finorchem Limited
9E, Saket Apartment, 2 Ho Chi Minh Sarani, 9th Floor
Kolkata-700 071
+91-33-40634254, Corporate@finorchem.com