

	FINORCHEM LIMITED			Doc. No.: FM12/PDS/ADL/009
	FINISHED PRODUCT- PDS			Page 1 of 1
	Issue No.: 02	Issue Date: 04/07/2024	Rev. No.: 01	Eff. Date: 05/07/2024

FINOREX RR-95

DESCRIPTION

Tall Oil modified phenol – formaldehyde Reinforcing resin

PRODUCT SPECIFICATION

Sr. No.	Property	Unit	Specification		Test Method
			Min	Max	
1.	Appearance	-	Brown colour Pastille/Flakes		Visual
2.	Softening point (R&B)	°C	90	110	ASTM E28
3.	Moisture content	%w/w	-	0.5	ASTM E203
4.	Ash content, 750±25°C	%w/w	-	0.5	ASTM D4574
5.	Specific Gravity at 25°C	-	1.11	1.21	ASTM D1817

RECOMMENDED APPLICATIONS:

Finorex RR-95 resin could be used as reinforcing agents for rubber compounds improves SBR compatibility and dispersibility, provide strong plasticizing action during processing without fear of scorching. Rubber compounds can improve the hardness, tear resistance, abrasion resistance, tensile strength, reduced Mooney viscosity and prolonged scorch time properties.

PACKAGING

25 Kg in HDPE liner with paper bag / carton packing.

STORAGE

Finorex RR-95 is a stable resin and can be stored for 12 months from the date of manufacture. under normal storage conditions. Need to store below 30°C in tight container away from heat and humidity.

OCCUPATIONAL SAFETY AND HEALTH INFORMATION

Refer to Material Safety Data Sheets (MSDS) prior to using this resin.

Corporate Office:

Finorchem Limited
9E, Saket Apartment, 2 Ho Chi Minh Sarani,
9th Floor Kolkata-700 071
+91-33-40634254, Corporate@finorchem.com