

	FINORCHEM LIMITED			Doc. No.: FM12/PDS/ADL/032
	FINISHED PRODUCT- PDS			Page 1 of 1
	Issue No.: 02	Issue Date: 04/07/2024	Rev. No.: 01	Eff. Date: 05/07/2024

FINOREX RS

DESCRIPTION

Resorcinol -silica blend & Resorcinol dispersion

PRODUCT SPECIFICATION

Sr. No.	Property	Unit	Specification		Test Method
			Min	Max	
1.	Appearance	-	Free flowing fine white powder		Visual
2.	Resorcinol content	%w/w	47	53	QC/STP/U2/145
3.	Ash content, 850±25°C	%w/w	42	48	ASTM D4574
4.	Fineness through 120 mess dry sieve	%w/w	98	-	ASTM D5461
5.	Specific Gravity at 25°C	-	1.50	1.70	ASTM D1817

RECOMMENDED APPLICATIONS

Finorex RS reduces fuming of resorcinol during Mixing. Form crosslinked structure during curing with HMMM, HMT and improved Bonding strength. Finorex RS use in tyres, vbelts, conveyor belt hoses and rubberized Fabric.

PACKAGING

25 Kg in HDPE liner with paper bag / carton packing.

STORAGE

Finorex RS is hygroscopic and must be protected from exposure to relative humidity. This product should be stored in a cool dry place. This material is stable for 12 months from the date of manufacturing.

OCCUPATIONAL SAFETY AND HEALTH INFORMATION

Refer to Material Safety Data Sheets (MSDS) prior to using this resin.

Corporate Office:

Finorchem Limited

9E, Saket Apartment, 2 Ho Chi Minh Sarani, 9th

Floor Kolkata-700 071

+91-33-40634254, Corporate@finorchem.com