

	FINORCHEM LIMITED			Doc. No.: FM12/PDS/ADL/014
	FINISHED PRODUCT- PDS			Page 1 of 1
	Issue No.: 02	Issue Date: 04/07/2024	Rev. No.: 01	Eff. Date: 05/07/2024

## FINOREX TP-115

### DESCRIPTION

- Terpene phenolic resin. Tread enhancement additive-TEA resin.

### PRODUCT SPECIFICATION

Sr. No.	Property	Unit	Specification		Test Method
			Min	Max	
1.	Appearance	-	Light yellow to reddish brown colour pastles/flakes		Visual
2.	Softening point (R&B)	°C	115	125	ASTM E28
3.	Ash content, 750±25°C	%w/w	-	0.50	ASTM D4574
4.	Loss on drying at 105°C	%w/w	-	0.50	ASTM D4571
5.	Acid value	mgKOH/gm	-	2.0	ASTM D1980
6.	Specific Gravity at 25°C	-	0.95	1.15	ASTM D1817

### RECOMMENDED APPLICATIONS

Finorex TP-115, modify the viscoelastic nature of polymer by increasing compound Tg and offers improved traction and marginal reduction in rolling resistance. Finorex TP-115 used in automobile tires, chloroprene & hot melt adhesives and pressure sensitive adhesives.

### PACKAGING

25 Kg in HDPE liner with paper bag / carton packing.

### STORAGE

Finorex TP-115 resin recommends storage temperatures below 35°C, this material is a stable resin and can be stored for 12 months from the date of manufacture.

### OCCUPATIONAL SAFETY AND HEALTH INFORMATION

Refer to Material Safety Data Sheets (MSDS) prior to using this resin.

#### Corporate Office:

Finorchem Limited  
9E, Saket Apartment, 2 Ho Chi Minh Sarani, 9<sup>th</sup> Floor  
Kolkata-700 071

+91-33-40634254, Corporate@finorchem.com