ACMEBOND HMMM 55

DESCRIPTION:

Hexamethoxymethylmelamine 55% active on precipitated silica. White free flowing powder.

PRODUCT SPECIFICATION:

Parameters	Specification			Reference Test Method
	Units	Min	Max	
Ash Content (at 800^{0}C for 2 hrs.)	%w/w	40.0	42.00	QC/STP/U1/02
Active Ingredient	%	54.0	56.0	QC/STP/U1/35
LOD (at 105^{0}C for 2 hrs.)	%w/w	--	5.00	QC/STP/U1/04
Sieve residue on 100 mesh	%w/w	--	0.50	QC/STP/U1/03
Free Formaldehyde	%w/w	--	0.20	QC/STP/U1/43

PACKAGING:

25 Kgs (nett) in Paper Bags with LDPE Inner Liner.

STORAGE:

1 years from the date of production provided
Preserved in cool and dry atmosphere in Closed original packaging.

OCCUPATIONAL SAFETY AND HEALTH INFORMATION:

Refer to Material Safety Data Sheets (MSDS) prior to using this resin.

Corporate Office :
Finorchem Limited
9E, Saket Apartment, 2 Ho Chi Minh Sarani,
9th Floor Kolkata-700 071
+91-33-40634254, Corporate@finorchem.com