FINOREX TP-115

DESCRIPTION

- Terpene Phenolic Resin. Tread Enhancement Additive-TEA Resin.

PRODUCT SPECIFICATION

Sr. No.	Property	Unit	Specification		Test Method
			Min	Max	
1	Appearance	-	Light yellow to reddish brown colour lumps/pastilles/flakes		Visual
2	Softening point (R&B)	°C	110	125	ASTM E28
3	Ash content, @750±25°C, 2 hrs.	%w/w	-	0.50	ASTM D4574
4	Loss on drying at 70°C, 2 hrs.	%w/w	-	0.50	ASTM D4571
5	Acid value	mg KOH/gm	-	2.0	ASTM D1980
6	Specific Gravity at 25°C	-	0.95	1.15	ASTM D1817

RECOMMENDED APPLICATIONS

Finorex TP-115 enhances the viscoelastic properties of polymers, improving traction, and slightly reducing rolling resistance. It is used in automobile tires, chloroprene, hot melt adhesives, and pressure-sensitive adhesives.

PACKAGING

25 Kg in HDPE liner with paper bag / carton packing.

STORAGE

Finorex TP-115 resin recommends storage temperatures below 35°C, this material is a stable resin and can be stored for 12 months from the date of manufacture.

OCCUPATIONAL SAFETY AND HEALTH INFORMATION

Refer to Material Safety Data Sheets (MSDS) prior to using this resin.

Corporate Office:
Finorchem Limited
9E, Saket Apartment, 2 Ho Chi Minh Sarani, 9th Floor
Kolkata-700 071

+91-33-40634254, Corporate@finorchem.com